

its full term is Poly-Lactic Acid and it is a thermoplastic polymer. Because it is derived from natural sources like corn and sometimes sugarcane, PLA is sometimes referred to a bioplastic. The majority of other thermoplastics are distilled from non-renewable resources like petroleum. In addition, because it is a natural product, it is also long-term biodegradable. This means that when discarded into a composting system, PLA will naturally break down into its constituent parts typically within a few years.

The matte finish PLA is also great for applications where it's essential to reduce reflectivity, for example, in making hoods and surrounds for camera lenses. And, perhaps most importantly, this finish also allows your designs to truly stand out. Fine details that would normally be glossed over by a regular, shiny PLA, are clear and unobscured

Pros

- Can be printed on a cold surface
- more environmental-friendly
- low light reflection

Cons

- Can deform because of heat
- Less sturdy

Uses

- Design
- Detailed prints

1. Identification of the material

Trade name	tm filament PLA Matt
Chemical name	Poly-Lactic Acid
Use	3D printing
Origin	tm filament Netherlands

2. Material properties

Melt temperature	145-160	°C	ASTM D3418
Glass transition temperature	55-60	°C	ASTM D3419
Heat distortion temperature HDTB (0,45 MPa)	56	°C	ISO 75
Vicat Softening Temperature	60	°C	ASTM D1525
Met Flow Rate (210 C/2.16 kg)	9,56	g	ASTM D1238
Density	1.24	g/cm ³	ASTM D790
Water absorption, 24 u	0.1	%	ASTM D570
Shrink rate	0.5 - 0.7	%	ASTM D955

3. Mechanical properties

Tensile Strength (break, 3.20 mm/50 mm/min)	52	MPa	ISO 527
Tensile Modulus (3.20 mm/1.0 mm/min)	1320	MPa	ISO 527
Tensile elongation, (break, 3.20 mm/50 mm/min)	5	%	ISO 527
Flexural Modulus (3.20 mm/15 mm/min)	3600	MPa	ISO 178
Flexural Strength (3.20 mm/15 mm/min)	108	MPa	ISO 178
Rockwell hardness (R-scale)	95		ASTM D785

4. Printer settings

Printer	Desktop FFF printer
Nozzle	0.4 mm A2 hardened
Layer height	0.2 mm
Infill	100% ±45
Extrusion Temperature	190 - 220 °C
Bed temperature	46 - 60 °C
Bed preparation	Kapton tape, Glass, 3D laque
Print speed	20-40 mm/sec
Requirements	Cooling fan

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.